

## OneWayPro<sup>®</sup> SEALING TAPE

### TECHNICAL DATA SHEET

*OneWayPro<sup>®</sup> SEALING TAPE is a permanent, long-lasting ultraclear adhesive tape designed for edge protection of self-adhesive films.*

#### **Specifications:**

The **OneWayPro<sup>®</sup> SEALING TAPE** is recommended for long-term edge protection of self-adhesive films such as OneWayPro<sup>®</sup> microperforated films. It improves resistance to temperature variations, mechanical peeling and shrinkage. The film is composed of a 50 µm ultraclear cast PVC with an ultraclear solvent-based adhesive, protected by a PET liner. It perfectly follows the relief of the protected edges.

#### **Uses:**

The **OneWayPro<sup>®</sup> SEALING TAPE** can be applied to the edges as well as to the joints between two adhesive films. Particular care should be taken not to apply the tape on silicone seals, as adhesion on silicone is very poor and may cause the tape to peel off.

#### **Durability:**

The durability of the product can be up to 10 years depending on exposure conditions.

#### **Storage:**

2 years – between 15 and 25°C and a humidity of 45 to 55% in the original packaging.

#### **Adhesion:**

Quick tack on glass: 15 N/25 mm ± 2.5 N/25 mm (FTM 9)

180° peel strength on glass after 20 minutes: 11 N/25 mm ± 2.5 N/25 mm (FTM 1)

180° peel strength on glass after 24 hours: 14 N/25 mm ± 2.5 N/25 mm (FTM 1)

Application temperature: 10° to 40°C

Operating temperature: -20°C to 80°C

# OneWayPro<sup>®</sup>

HIGH QUALITY ONE WAY VISION

## Instructions for use:

You will find a file on our website under the tab "Tips for use" with important information for the use of our products.

## Product references:

<b>SEALING TAPE</b>	<b>50 µm</b>	<b>PET Liner</b>	<b>9 mm x 50 m</b>	SEALING-TAPE-0009050
---------------------	--------------	------------------	--------------------	----------------------

## Note:

The information contained in this brochure is based on laboratory tests and experience we have gained in practice. They could not provide a legal guarantee. A preliminary test on the material is to be made. Sustainability is estimated from the exposure conditions in Central Europe. The actual life of the product depends on substrate preparation, exposure conditions and maintenance of the marking. We can expect performance degradation outside when the films are exposed to the south, if they are applied in areas where the temperature is often high as countries of southern Europe, or in polluted areas.